



AlSi7 Mg0.6

Typical Mechanical Properties

| | |
|---------------------------|---------|
| Ultimate tensile strength | 412 MPa |
| Yield strength | 287 MPa |
| Elongation at break | 9% |

Process Parameter



Aluminium Based Alloy

An aluminium-based alloy common for laser powder bed fusion, which can be used in place of traditionally cast applications and for prototypes and functional parts.

Highlights

- Good mechanical properties
- Good corrosion resistance
- Good thermal & electrical conductivity
- Applications in aerospace, automotive and industrial sectors
- Used in place of castings and for heat management parts such as heat exchangers
- Layer thickness: 60µm
- Density >99.8%
- Good productivity
- Minimum controlled features 0.6mm

Process Readiness Level (PRL)

| | | | | | | | | |
|-----|---|---|---|------------|---|------------|---|---|
| R&D | | | | Foundation | | Production | | |
| 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | 9 |

AlSi7 Mg0.6

Aluminium Based Alloy

To learn more,
contact us: info@additiveindustries.com

or visit:
additiveindustries.com

Powder Chemistry^[2,3]

| Composition | Al | Si | Fe | Cu | Mn | Mg | Zn | Ti | O | Other | All Other |
|-------------|-----|------|------|------|------|------|------|------|-------|-------|-----------|
| Min (wt%) | Bal | 6.50 | - | - | - | 0.45 | - | - | - | - | - |
| Max (wt%) | Bal | 7.50 | 0.19 | 0.05 | 0.10 | 0.70 | 0.07 | 0.25 | 0.035 | 0.03 | 0.10 |

Process details

| | | |
|---------------------------------------|--------|----------|
| Layer thickness | 60 | [µm] |
| Build rate ^[6] (per laser) | 39 | [cm3/hr] |
| Optical density ^[4] | ≥ 99.8 | [%] |
| Volumetric density ^[11] | ≥ 2.67 | [g/cm3] |

©2024 Additive Industries B.V.
All rights reserved.

Specifications are subject to change without notice. Additive Industries is certified in accordance with ISO 9001

Additive Industries B.V. Headquarters, Eindhoven, The Netherlands
T: +31 (0)40 2180660

Additive Industries North America, Inc. Camarillo, United States of America
T: +1 805 530 6080

| Mechanical properties ^[5] | Orientation | As-built (Mean) | Standard Dev. | Heat-treat (Mean) | Standard Dev. | Units |
|--------------------------------------|-------------|-----------------|---------------|-------------------|---------------|--------|
| Ultimate tensile strength | Horizontal | 412 | 5 | - | - | [MPa] |
| | Vertical | 406 | 5 | - | - | [MPa] |
| Yield strength | Horizontal | 287 | 5 | - | - | [MPa] |
| | Vertical | 242 | 5 | - | - | [MPa] |
| Elongation at break | Horizontal | 9 | 1 | - | - | [%] |
| | Vertical | 7 | 1 | - | - | [%] |
| Youngs modulus | Horizontal | 69 | 5 | - | - | [GPa] |
| | Vertical | 67 | 5 | - | - | [GPa] |
| Vickers Hardness ^[6] | | 121 | 5 | - | - | [HV10] |

| Surface Roughness ^[7] | Mean | Standard Deviation | Units |
|----------------------------------|------|--------------------|-------|
| Vertical Surface Roughness (Ra) | 13.4 | 2 | [µm] |
| Vertical Surface Roughness (Rz) | 69.4 | 10 | [µm] |
| 45° Surface Roughness (Ra) | - | - | [µm] |
| 45° Surface Roughness (Rz) | - | - | [µm] |

Notes

1. The material is processed under Argon shielding atmosphere.

2. Powder Chemistry as per Additive Industries specification O2907 Rev. 2.0.

3. Additive Industries consolidated material is in compliance with literature at the time of publication.

4. Density measured by Optical Measurement Method as per internal process. This is the minimum guaranteed value that is achieved under standard processing conditions, manufactured using Additive Industries' qualification jobs.

5. Tensile test samples were produced as round blanks. These were machined to size and tested in accordance with ASTM E8m at a NADCAP approved supplier.

6. Hardness measured in accordance with DIN EN ISO6507-1:2018 as per internal process. Hardness values measured in XY and XZ planes from components manufactured using Additive Industries' qualification jobs.
7. Surface Roughness measured in as-printed condition in accordance with internal process. Roughness measurement conducted on specimens with varying unsupported manufacturing angle.

8. Build Rate stated is a typical value per laser. It is calculated using the formula: Layer Thickness x Laser Scan Speed x Hatch Distance.

9. Parameter released: AS7_60_BAL_MF1A64_INT_1.0.

10. Heat Treatment : NA

11. Volumetric density measured according to ASTM B962. This is a minimum volumetric density measurement achieved on samples manufactured using Additive Industries' qualification jobs.

12. Minimum part thickness for which reported optical density is to be expected.





Disclaimer

The data presented in this material datasheet is valid only for Additive Industries' released powder, machine, and parameter sets, processed under the defined shielding atmosphere. The properties of the printed parts have been measured on test coupons according to industry standards where available, and the data correspond to our state-of-the-art at the time of publication. These results are based on Additive Industries' signoff build layout and reflect material performance under the specified conditions; for more information, please contact Additive Industries. Users should be aware that variations in the presented values may arise due to differences in process conditions, including but not limited to thermal management, build plate temperature, job-specific heat accumulation, inter-layer time, part positioning, and overall machine calibration. The data provided do not warrant any guarantee for printed parts, and it remains the responsibility of the producer or purchaser to verify the ultimate properties of the printed material for their specific application. The listed data are subject to change without notice as we continuously strive to develop and improve our machine performance and the properties of printed materials. Users are advised to exercise caution and consider material selection, build layout, and machine configuration when interpreting and applying this information.

©2025 Additive Industries B.V.
All rights reserved.

Specifications are subject to change without notice. Additive Industries is certified in accordance with ISO 9001

Additive Industries B.V. Headquarters, Eindhoven,
The Netherlands
T: +31 (0)40 2180660

Additive Industries
North America, Inc.
Camarillo, United States of America
T: +1 805 530 6080

To learn more,
contact us: info@additiveindustries.com

or visit:
additiveindustries.com